



## FORMWORX

Formworx Latex Block Filler  
05700



### COMPLIANCE INDICATORS

at 04/05/2016

MPI #4

### DESCRIPTION

A contractor/maintenance, Interior/Exterior, heavy bodied blockfiller designed to fill voids and reduce irregularities on new concrete block and other types of masonry. This product meets the United States Environmental Protection Agency national volatile organic compound emission standards for architectural coatings. Approved by the Master Painter's Institute under category # 4. Meets the standard for CAN/CGSB - 1.188 - M90. ( Qualification #80147) Environment Canada VOC compliant.

### RECOMMENDED USES

Use on concrete block, cinder block, cement block and other types of masonry. Apply only at temperatures above 10°C (50°F).

### FEATURES

A heavy bodied, interior/ exterior latex undercoat designed to fill voids and smooth irregularities on new concrete block and other masonry surfaces. Helps reduce the porosity and seal masonry surfaces prior to painting. Reduces the penetration of finish coats providing for less paint consumption and an even sheen.

### TECHNICAL CHARACTERISTICS

<b>Bases</b>	<b>VOC(g/L)*</b>
--------------	------------------

White Primer (05700)	< 45
----------------------	------

*\*Before thinning and the addition of colorants*

### FINISH

Gloss Category: Gloss Level 0 - Primer-Sealer-Undercoat

### SOLIDS & DENSITY

Volume: 50%

Weight: 69%

Density:

### FILM THICKNESS (PER COAT)

Wet: 12.8 - 21.4 mils (325 - 544 microns)

Dry: 7.0 - 12.0 mils (178 - 305 microns)

### THEORETICAL COVERAGE (PER COAT)

65 - 115 ft<sup>2</sup> per gallon (1.6 - 2.8 m<sup>2</sup>/L)

### VISCOSITY

110 - 120 KU

### DRYING TIME

at 25°C (77°F) and 50% Relative Humidity

Tack Free: 45 minutes

Re-Coat: 2 hours

### REDUCERS

Not normally recommended.





## SURFACE PREPARATION

Surface preparation is important. All surfaces must be smooth, clean, dry, free of mildew, grease, soap film, sanding dust or other contaminants. Remove all loose or peeling material from previously-painted surfaces. Wash all surfaces with a solution of 3 tablespoons of (Phosphate-free) TSP in a gallon of warm water. Rinse thoroughly, allow to dry and then scuff sand using 80-120 grit sandpaper on a hand sander. Remove all sanding dust. Do not apply at temperatures below 10°C (50°F).

**WARNING!** If you scrape, sand or remove old lead paint from any surface you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. For additional information, Canadian customers contact the Product Safety division of Health Canada at 1-800-O-CANADA, US customers contact the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323).

## Application Equipment

Stir well before and during use. Best results are achieved when using a heavy pile roller or power roller system. Airless spray application accompanied with back rolling is also a recommended application technique. Recommended tip sizes: 0.023"- 0.029". Always apply coating at the recommended spread rate.

## SAFETY PRECAUTIONS

*For detailed information please refer to SDS*

**First Aid:** In case of eye contact, flush immediately with plenty of water for at least 15 minutes. Wash contaminated skin with soap and water. If ingested, call physician or the Poison Control Centre immediately.

## READ LABEL AND SAFETY DATA SHEET PRIOR TO USE.

### Recent Amendments

Check for recent amendments to this data sheet at [www.cloverdalepaint.com](http://www.cloverdalepaint.com)

**Last Modification date:** 08/11/2025

## LIMITATION OF LIABILITY

To the best of our knowledge, the technical data contained herein are true and accurate at the time of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. All technical advice, recommendations and services regarding this product are rendered by the Seller gratis. They are based on technical data which the Seller believes to be reliable and are intended for use by persons having skill and know-how, at their discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from this product use by Buyer whether as recommended herein or otherwise. Such recommendations, technical advice or services are not to be taken as a license to operate under or suggest infringement of any patent.

## WARRANTY

Cloverdale Paint Inc. warrants its products to be free from defects in material and workmanship. At its option, Cloverdale Paint Inc. will either replace products not conforming to this warranty or credit the Buyer's account the invoiced amount for the non-conforming products. This is Cloverdale Paint Inc.'s sole obligation and Buyer's exclusive remedy in connection with the products. In no event shall Cloverdale Paint Inc. be liable for special, indirect, consequential or incidental damages.

By purchasing this product the Buyer accepts this warranty in lieu of all others, and waives all claims to any other remedy arising from any warranty or guarantee of quality, whether such warranty or guarantee of quality was made expressly to the Buyer or implied by any applicable law.

Any claim under this warranty must be made in writing by the Buyer to Cloverdale Paint Inc. within ten (10) days of discovery of the claimed non-conformance, but in no event later than one (1) year from the delivery date. The Buyer's failure to notify Cloverdale Paint Inc. of such non-conformance as required herein shall bar the Buyer from recovery under this warranty.

